



## DTT-N50

特性 Characteristics	单位	N50
初始磁导率 $\mu_i$ Initial permeability	—	500 ± 25%
工作频率 f Working Frequency	MHz	0.1–1.5
比损耗因子 $\tan \delta / \mu_i^*$ Relative loss factor	$\times 10^{-6}$	55 ( 0.1MHz )
饱和磁通密度 $B_s^*$ Saturation flux density	mT	460 ( 4000A/m )
剩磁 $B_r^*$ Remanent flux Density	mT	320
矫顽力 $H_c^*$ Coercive force	A/m	37
比温度系数 $\alpha \mu r^*$ Relative temperature Coefficient	$\times 10^{-6}/^{\circ}\text{C}$ 20°C~60°C	10–30
居里温度 $T_c$ Curie temperature	°C	> 240
电阻率 $\rho^*$ Resistivity	$\Omega \cdot \text{m}$	> 10 <sup>5</sup>
密度 D* Density	g/cm <sup>3</sup>	5.20

注：本页数据是根据标准样环  $\Phi 25 \times \Phi 15 \times 8$  获得的典型数据，有关产品的具体性能会在此基础上有所调整。

The typical data are calculated from the standard toroid core. The specific property of any parts will be adjusted a little based on these data.

